

# ciclo di VERNICIATURA a POLVERE

Step	TREATMENT	TIME	TEMP.	pH	PRODUCT
1	Charge		Ambient		
2	Cooling		Ambient		
3	<b>Application P.V.</b>		Ambient		
4	<b>Polymerization</b>	<b>24 min</b>	<b>180 - 190°C***</b>		
5	Colling		Ambient		
6	Descharge		Ambient		
7	Visual control		Ambient		
8	Packaging		Ambient		

\*\*\* object temperature